

AFWAL-TR-80-4109

12



LEVEL

DEVELOPMENT OF MIL-HDBK-5 DESIGN ALLOWABLE PROPERTIES FOR SEVERAL AEROSPACE MATERIALS

AD A091602

PAUL E. RUFF
BATTELLE'S COLUMBUS LABORATORIES
505 KING AVENUE
COLUMBUS, OHIO 43201

DTIC
SELECTED
NOV 13 1980
S D

C

AUGUST 1980

TECHNICAL REPORT AFWAL-TR-80-4109
FINAL REPORT FOR THE PERIOD 25 APRIL 1977-29 AUGUST 1980

Approved for public release; distribution unlimited.

DDC FILE, WGT 4

MATERIALS LABORATORY
AIR FORCE WRIGHT AERONAUTICAL LABORATORIES
AIR FORCE SYSTEMS COMMAND
WRIGHT-PATTERSON AIR FORCE BASE, OHIO 45433

80 11 07 116

NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

This report has been reviewed by the Office of Public Affairs (ASD/PA) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nations.

This technical report has been reviewed and is approved for publication.

C. J. Harmsworth
C. J. Harmsworth, Technical Manager
for Engineering and Design Data
Materials Integrity Branch
Systems Support Division
Air Force Wright Aeronautical Laboratory

FOR THE COMMANDER

T. D. Cooper
T. D. Cooper, Chief
Materials Integrity Branch
Systems Support Division
Air Force Wright Aeronautical Laboratory

If your address has changed, if you wish to be removed from our mailing list, or if the addressee is no longer employed by your organization please notify AFWAL/MLSA WPAFB, OH 45433 to help us maintain a current mailing list.

Copies of this report should not be returned unless return is required by security considerations, contractual obligations, or notice on a special document.

⑨ Final rept. 29 Apr 77 - 29 Aug 80

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

19 REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1 REPORT NUMBER AFWAL-TR-80-4189	2 GOVT ACCESSION NO. AD-A094	3 RECIPIENT'S CATALOG NUMBER 602	
4 TITLE (and Subtitle) Development of MIL-HDBK-5 Design Allowable Properties for Several Aerospace Materials		5 TYPE OF REPORT & PERIOD COVERED Final, April 25, 1977 - August 29, 1980	6 PERFORMING ORG. REPORT NUMBER
7 AUTHOR(s) Paul E. Ruff		8 CONTRACT OR GRANT NUMBER(s) F33615-77-C-5036 (r w)	
9 PERFORMING ORGANIZATION NAME AND ADDRESS Battelle's Columbus Laboratories 505 King Avenue Columbus, Ohio 43201		10 PROGRAM ELEMENT PROJECT TASK AREA & WORK UNIT NUMBERS FY 1457	
11 CONTROLLING OFFICE NAME AND ADDRESS Materials Lab, Air Force Wright Aeronautical Lab Air Force Systems Command Wright-Patterson Air Force Base, Ohio 45433		12 REPORT DATE August 1980	
14 MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) DCASMA, Dayton Defense Electronics Supply Center Building 5, 1502 Wilmington Pike Dayton, Ohio 45444		13 NUMBER OF PAGES 84	15 SECURITY CLASS (of this report) Unclassified
16 DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		15a DECLASSIFICATION DOWNGRADING SCHEDULE	
17 DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18 SUPPLEMENTARY NOTES			
19 KEY WORDS (Continue on reverse side if necessary and identify by block number) tensile yield strength bearing yield strength tensile ultimate strength bearing ultimate strength compressive yield strength compressive modulus of elasticity shear ultimate strength			
20 ABSTRACT (Continue on reverse side if necessary and identify by block number) This final report describes a test program to determine MIL-HDBK-5 design allowable properties for 2024-T42 extrusion and Ti-6Al-2Sn-4Zr-2Ni, duplex annealed, sheet.			

407080

115

PREFACE

This final report was submitted by Battelle's Columbus Laboratories, 505 King Avenue, Columbus, Ohio 43201, under Contract F33615-77-C-5036 with the Air Force Wright Aeronautical Laboratory, Wright-Patterson Air Force Base, Ohio. Mr. C. L. Harmsworth (MLSA) was the laboratory project monitor. This report covers the period of work from April 25, 1977, through August 29, 1980. This report was submitted by the author, Mr. Paul E. Ruff, in August 1980.

Accession For	
RTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	<input type="checkbox"/>
By _____	
Distributor/	
Availability Codes	
Dist	Avail and/or Special
R	

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
OBJECTIVE	1
EXPERIMENTAL PROCEDURES	2
2024-T42 Aluminum Alloy Extrusion.	2
Ti-6Al-2Sn-4Zr-2Mo Titanium Alloy Sheet.	47
APPENDIX A - TEST PROCEDURES.	83

LIST OF ILLUSTRATIONS

	<u>Page</u>
FIGURE 1. TENSILE SPECIMEN.	27
2. COMPRESSION SPECIMEN.	28
3. SHEAR SPECIMEN.	29
4. BEARING SPECIMEN.	29
5. LOCATION OF LONG TRANSVERSE SPECIMENS FOR 1" x 2-1/2" BAR	30
6. LOCATION OF LONGITUDINAL SPECIMENS FOR 1" x 2-1/2" BAR.	30
7. LOCATION OF TRANSVERSE SPECIMENS FOR 1-1/4" x 2-1/4" BAR.	31
8. LOCATION OF LONGITUDINAL SPECIMENS FOR 1-1/4" x 2-1/4" BAR.	31
9. LOCATION OF LONG TRANSVERSE SPECIMENS FOR 1-1/2" x 2-1/2" BAR	32
10. LOCATION OF LONGITUDINAL SPECIMENS FOR 1-1/2" x 2-1/2" BAR.	32
11. LOCATION OF LONG TRANSVERSE SPECIMENS FOR 2" x 2" BAR	33
12. LOCATION OF LONGITUDINAL SPECIMENS FOR 2" x 2" BAR.	33
13. LOCATION OF LONG TRANSVERSE SPECIMENS FOR 1-3/4" x 3" BAR	34
14. LOCATION OF LONGITUDINAL SPECIMENS FOR 1-3/4" x 3" BAR.	34
15. LOCATION OF LONGITUDINAL SPECIMENS FOR ANGLE.	35
16. LOCATION OF LONG TRANSVERSE SPECIMENS FOR ANGLE	35
17. LOCATION OF LONGITUDINAL SPECIMENS FOR ZEE.	36
18. LOCATION OF LONG TRANSVERSE SPECIMENS FOR ZEE	36
19. PLOT OF TUS (LT)/TUS (L) RATIOS	37
20. PLOT OF TYS (LT)/TYS (L) RATIOS	38
21. PLOT OF CYS (L)/TYS (L) RATIOS.	39
22. PLOT OF CYS (LT)/TYS (L) RATIOS	40
23. PLOT OF SUS (L)/TUS (L) RATIOS.	41
24. PLOT OF SUS (LT)/TUS (L) RATIOS	42
25. PLOT OF BUS (L)/TUS (L), e/D = 1.5, RATIOS	43
26. PLOT OF BYS (L)/TYS (L), e/D = 1.5, RATIOS	44
27. PLOT OF BUS (L)/TUS (L), e/D = 2.0, RATIOS	45
28. PLOT OF BYS (L)/TYS (L), e/D = 2.0, RATIOS	46
29. TENSILE SPECIMEN.	70
30. COMPRESSION SPECIMEN.	70
31. SHEAR SPECIMEN.	71
32. BEARING SPECIMEN.	71
33. LOCATION OF TEST SPECIMENS, 0.030, 0.040, 0.055, 0.063, AND 0.071-INCH THICK SHEET.	72
34. LOCATION OF TEST SPECIMENS, 0.050 AND 0.080-INCH THICK SHEET	73
35. LOCATION OF TEST SPECIMENS, 0.090-INCH THICK SHEET.	74
36. LOCATION OF TEST SPECIMENS, 0.100-INCH THICK SHEET.	75
37. LOCATION OF TEST SPECIMENS, 0.125-INCH THICK SHEET.	76
38. PLOT OF BUS (LT)/TUS(LT), e/D = 1.5, RATIOS	77
39. PLOT OF BUS(LT)/TUS(LT), e/D = 2.0, RATIOS.	78
40. WORKING CURVE SHOWING THE EFFECT OF TEMPERATURE ON COMPRESSIVE YIELD STRENGTH OF TI-6AL-2SN-4ZR-2MO DUPLEX ANNEALED SHEET.	79
41. PROPOSED MIL-HDBK-5 FIGURE 5.3.3.2.1.	80
42. COMPARISON OF E _c PERCENTAGES WITH EXISTING E CURVE.	81
43. PROPOSED MIL-HDBK-5 FIGURE 5.3.3.1.4.	82

LIST OF TABLES

	<u>Page</u>
TABLE 1. TEST PLAN FOR 2024-T42 EXTRUSIONS	6
2. MECHANICAL PROPERTIES OF 2024-T42 EXTRUSIONS.	7
3. TENSILE, COMPRESSION, SHEAR, AND BEARING RATIOS FOR 2024-T42 EXTRUSIONS	8
4. LIST OF RATIOS VERSUS THICKNESS FOR 2024-T42 EXTRUSIONS	9
5. LIST OF RATIOS VERSUS THICKNESS FOR 2024-T42 EXTRUSIONS	12
6. LIST OF RATIOS VERSUS THICKNESS FOR 2024-T42 EXTRUSION.	15
7. LIST OF RATIOS VERSUS THICKNESS FOR 2024-T42 EXTRUSION.	18
8. LIST OF RATIOS VERSUS THICKNESS FOR 2024-T42 EXTRUSION.	21
9. COMPUTED REDUCED RATIOS FOR 2024-T42 EXTRUSIONS	24
10. PROPOSED MIL-HDBK-5 TABLE 3.2.3.0(j ₂)	25
11. PROPOSED MIL-HDBK-5 TABLE 3.2.3.0(j ₁)	26
12. TEST PLAN FOR TI-6AL-2SN-4ZR-2MO SHEET.	51
13. MECHANICAL PROPERTIES OF TI-6AL-2SN-4ZR-2MO SHEET	52
14. LIST OF RATIOS VERSUS THICKNESS FOR TI-6AL-2SN-4ZR-2MO.	56
15. LIST OF RATIOS VERSUS THICKNESS FOR TI-6AL-2SN-4ZR-2MO.	59
16. LIST OF RATIOS VERSUS THICKNESS FOR TI-6AL-2SN-4ZR-2MO.	62
17. REDUCED RATIOS FOR TI-6AL-2SN-4ZR-2MO SHEET	65
18. E _c /E RATIOS FOR TI-6AL-2SN-4ZR-2MO SHEET.	66
19. EFFECT OF TEMPERATURE ON COMPRESSIVE YIELD STRENGTH OF TI- 6AL-2SN-4ZR-2MO SHEET	67
20. EFFECT OF TEMPERATURE ON COMPRESSIVE MODULUS OF TI-6AL-2SN- 4ZR-2MO SHEET	68
21. PROPOSED MIL-HDBK-5 TABLE 5.3.3.0(b).	69

SUMMARY

The results of this test program indicated that the existing design values in MIL-HDBK-5C for 2024-T42 extrusion are not appropriate for all thicknesses. Most of the existing "derived" properties, $F_{tu}(LT)$, $F_{ty}(LT)$, F_{cy} , F_{su} , F_{bru} , and F_{bry} , are unconservative above one-inch thickness with some of the existing values unconservative below this thickness. Consequently, new design allowable properties for 2024-T42 extrusion were determined in one-quarter-inch increments through $2\frac{1}{2}$ inches thickness and are presented in Table 10. These new design values were based upon the data obtained from this test program and existing data. The data were analyzed in accordance with MIL-HDBK-5 guidelines.

Based upon the data from this test program and existing data, missing design values for Ti-6Al-2Sn-4Zr-2Mo, duplex annealed, sheet, have been determined. Specifically, design values for F_{cy} , F_{bru} , and F_{bry} have been developed for four thickness ranges for sheet (0.187-inch maximum thickness) and are shown in Table 21. A room temperature E_c value, and an elevated temperature curve, Figure 43, for E_c , were established. Also, an elevated temperature curve, Figure 41, for F_{cy} was also determined.

These new design data have been prepared in MIL-HDBK-5 format to facilitate incorporation in the next MIL-HDBK-5 revision.

LIST OF SYMBOLS

R	=	reduced ratio, cyclic stress ratio
\bar{r}	=	mean value of ratios
s	=	standard deviation
$t_{0.95}$	=	the 0.95 fractile of the t distribution corresponding to n-1 degrees of freedom
n	=	number of ratios in sample
RT	=	room temperature
F_{tu}	=	ultimate tensile stress (design allowable)
F_{ty}	=	tensile yield stress (design allowable)
F_{cy}	=	compressive yield stress (design allowable)
F_{su}	=	ultimate shear stress (design allowable)
F_{bru}	=	ultimate bearing stress (design allowable)
F_{bry}	=	bearing yield stress (design allowable)
E	=	modulus of elasticity in tension
E_c	=	modulus of elasticity in compression
TUS	=	tensile ultimate strength
TYS	=	tensile yield strength
CYS	=	compressive yield strength
SUS	=	shear ultimate strength
L	=	longitudinal
LT	=	long transverse
BUS	=	bearing ultimate strength
BYS	=	bearing yield strength
ksi	=	thousands of pounds per square inch
psi	=	pounds per square inch

INTRODUCTION

The Military Standardization Handbook, MIL-HDBK-5, is recognized as the primary source for design allowable data required by the Department of Defense (DoD), other Government agencies, and aerospace contractors responsible for aerospace vehicle design. The Handbook contains design allowable data on metallic materials, fasteners, joints, and other structural elements. The maintenance of this document is achieved through the cooperative efforts of the Air Force, Navy, Army, Federal Aviation Agency (FAA), and industrial users and suppliers of metallic aerospace materials. The DoD has designated the Air Force as the activity responsible for preparing this Handbook. As such, the Air Force Wright Aeronautical Laboratory (AFWAL) has contracted with Battelle's Columbus Laboratories (BCL) to provide the planning, coordination, implementation, and testing necessary to develop and maintain current design allowable data and other related information in MIL-HDBK-5.

Other final reports have described in detail the functional and technical activities performed by BCL in connection with the MIL-HDBK-5 program. Since the functional as well as some of the technical activities are somewhat repetitive from year to year, this final report describes an experimental test program to develop certain MIL-HDBK-5 design allowable properties for several materials.

Most of the design allowable properties in MIL-HDBK-5 are determined from existing data. However, frequently data are lacking or inadequate to establish needed design properties. Data may be lacking for important design properties even though an alloy may have been used in the aerospace industry for many years. Sometimes it is desirable to verify existing design values in the Handbook. In addition, new heat treatments and new product forms may be developed for an existing alloy, thereby creating a need for applicable design properties. Also, MIL-HDBK-5 guidelines are continuously revised to provide for the inclusion of new types of data, such as fracture toughness and fatigue-crack-propagation data. For these reasons testing is often necessary to supplement data available from the literature.

Based upon interest expressed by the MIL-HDBK-5 Coordination Committee, availability of existing mechanical property data, and the availability of test material, two materials, 2024-T42 aluminum extrusion and Ti-6Al-2Sn-4Zr-2Mo, duplex annealed sheet were selected for this test program.

OBJECTIVE

The objective of this test program was : (1) to verify the existing room temperature design values for 2024-T42 extrusion and (2) to determine missing design values for Ti-6Al-2Sn-4Zr-2Mo, duplex annealed, sheet.

EXPERIMENTAL PROCEDURES

2024-T42 Aluminum Alloy Extrusion

Background - MIL-HDBK-5 currently contains in Table 3.2.3.0(j) a single set of design values which are applicable to all thicknesses for 2024-T42 extrusions. From this same table it is evident that the $F_{tu}(LT)/F_{tu}(L)$ and the $F_{ty}(LT)/F_{ty}(L)$ ratios decrease significantly with increasing thickness for 2024-T4, T3510, and T3511 extrusions. It is believed that these ratios should follow this same trend for the T42 temper.

Investigations revealed that design values for the T42 temper first appeared in MIL-HDBK-5, dated March 1959, which included items approved at meetings 1 through 16. However, a review of the agenda and minutes of these meetings did not reveal the basis for these design values. It appears that the bearing ratios were based upon a "rule-of-thumb", which was sometimes used for aluminum alloys at that time, as follows: $F_{bru}/F_{tu}(e/D = 1.5) = 1.5$, $F_{bru}/F_{tu}(e/D = 2.0) = 1.9$, $F_{bry}/F_{ty}(e/D = 1.5) = 1.4$, and $F_{bry}/F_{ty}(e/D = 2.0) = 1.6$. Item 66-20, "Derived Properties for Heat-Treated-By-User Tempers", was established at the 33rd meeting. Proposals containing design allowables were to be prepared based upon a forthcoming Air Force Materials Laboratory report, providing additional data could be obtained. Since additional data were not available, this item was cancelled.

A literature search revealed that tensile, compression, shear, and bearing data for 2024-T42 extrusions were contained in reference (1), presumably the report mentioned in Item 66-20. However, only five lots were tested in reference (1). Consequently, testing of additional lots was required in order to comply with MIL-HDBK-5 guideline requirements for the determination of design values. Since the basis for existing design values for the T42 temper could not be determined and the likelihood that the existing values were based upon limited data, it was desirable to conduct a test program to resolve this matter.

Test Plan - As defined in Chapter 1, Section 1.4.1.3 of MIL-HDBK-5, derived values are those room temperature mechanical property values that are established through their relationship to directly calculated (or specification) values for room temperature F_{tu} and F_{ty} . The guidelines for the presentation of data are described in Chapter 9, Section 9.2.9.1, of MIL-HDBK-5 and requires at least ten pairs of measurements, each representing a single lot of material.

-
- (1) Brownhill, D.J., et al, "Mechanical Properties, Including Fracture Toughness and Fatigue, and Resistance to Stress Corrosion Cracking, of Stress-Relieved Stretched Aluminum Alloy Extrusions", AFML-TR-58-34, Alcoa, February 1978, MCIC No. 71819.

Table 1 shows the test plan to acquire the necessary data. Room temperature tensile, compression, and bearing data for five lots (heats) were available in reference (1). Shear data were available for three lots in longitudinal direction and two lots in long transverse direction in reference (1). The data in reference (1) covered the following thicknesses: 0.064, 0.083, 0.430, 0.500, and 2.562 inches. Therefore, to span the thickness range through 2.562 inches, seven lots of extrusions preferably between 0.500 and 2.562 inches in thickness were needed. A request was made to aerospace companies participating in the MIL-HDBK-5 program for test material. Since the T42 temper is a "heat-treated-by-user temper", it was believed that representative T42 material would be obtained from aerospace companies.

Material - Only the Boeing Company could supply test material. Seven heats of extrusions in various thicknesses were received from Boeing as follows:

<u>Size, in.</u>	<u>Shape</u>	<u>Supplier</u>	<u>Lot No.</u>
1 x 2-1/4	Rectangle	Alcoa	389719
1-1/4 x 2-1/4	Rectangle	Alcoa	---
1-1/2 x 2-1/2	Rectangle	Alcoa	356925
1-3/4 x 3	Rectangle	Martin Marietta	89/551089
2 x 2	Square	Alcoa	354753
5/16 x 2 x 3	Angle	Alcoa	E93641A
---	Zee	Conalco	93162P-N

The test material was produced to QQ-A-220/3 and represented three suppliers. Boeing heat treated the extrusions to the T42 temper.

Test Specimens - Since single tests were used in reference (1), single tests were utilized in this program so as to avoid bias of the data. The configurations of the test specimens are shown in Figures 1 through 4. Because of the size and configuration of the extrusions, subsized test specimens were required. In order to minimize test variables, the configuration and size of the test specimens were similar to those used in reference (1). Longitudinal specimens were machined from the following locations:

Thickness, in.	Thickness	Location of Axis of Specimen With Respect To Thickness (T) and Width (W) of Predominant Section	
		Width	
		< 1.500 in.	> 1.500 in.
< 0.500	T/2	---	---
0.500 to 1.500 incl.	T/2	W/2	W/4
> 1.500	T/4	---	W/4

All long transverse specimens were taken from the T/2 location. These specimen locations were the same as those used in reference (1). Specific locations of the test specimens are shown in Figures 5 through 18.

Testing - All specimens were tested at room temperature in the "as received" T42 temper in accordance with the procedures described in Appendix A. The results of the mechanical property tests are shown in Table 2. All lots conformed to the minimum longitudinal tensile properties specified in CQ-A-200/3.

Analysis - As previously indicated, derived values refer to those room temperature mechanical property values that are established through their relationships to directly calculated (or specification) values for room temperature F_{tu} and F_{ty} . The procedure is applicable to F_{cy} , F_{su} , F_{bru} , and F_{bry} and involves the pairing of SUS and BUS measurements with TUS measurements for which F_{tu} has been established. Likewise, CYS and BYS measurements are paired with TYS measurements for which F_{ty} has been established. Tensile properties in grain directions not covered by specification are also derived in a similar manner.

Using the above relationships, reduced ratios for the various "unknown" properties were determined using the computational procedure described in Chapter 9, Section 9.2.9.2 of MIL-HDBK-5. The specified test direction for extrusions is longitudinal. Consequently, the individual test values for longitudinal and long transverse compression yield and bearing yield strength were paired with the corresponding individual test values for longitudinal tensile yield strength. Similarly, the longitudinal and long transverse shear and bearing ultimate values were paired to the corresponding longitudinal tensile ultimate values. Long transverse tensile yield and ultimate strength values were paired to corresponding longitudinal tensile properties. The tensile, compression, shear and bearing ratios are shown in Table 3 for the material tested. Reduced ratios were computed using the following equation when the ratios did not vary with thickness:

$$R = \bar{r} - \frac{t_{0.95}s}{\sqrt{n}}$$

where R = reduced ratio

\bar{r} = average of n ratios

s = standard deviation of the ratios

$t_{0.95}$ = the 0.95 fractile of the t distribution corresponding to n-1 degrees of freedom

n = number of ratios.

When the ratio varied with thickness, the following equation was used in regression analysis:

$$R = \bar{r}' - t_{0.95}s' \sqrt{\frac{1}{n} + \frac{(x_0 - \Sigma x/n)^2}{(\Sigma x^2) - (\Sigma x)^2/n}}$$

where R = reduced ratio

\bar{r}' = mean ratio for specific thickness, x_0

s' = standard error of estimate

$t_{0.95}$ = the 0.95 fractile of the t distribution corresponding to n-2 degrees of freedom

n = number of ratios

x_0 = specific thickness

x = individual thickness values for ratios.

A computer program was used to perform the analysis. The results are shown in Tables 4 through 8. A plot of ratio versus thickness is depicted in Figures 19 through 28. A summary of the computed reduced ratios is presented in Table 9.

All of the reduced ratios, except CYS(L)/TYS(L) and SUS(L)/TUS(L), exhibited regression with increasing thickness. Due to the severity of the regression for some properties, it was decided to present design values in 1/4-inch increments up to 2-1/2 inches in thickness. The reduced ratios in Table 9 were multiplied by the TUS(L) or TYS(L) specification value to obtain the design values shown in Table 10. Normally, shear and bearing allowables are not shown by grain direction. The lower reduced ratio for either grain direction was used to compute the design value for shear ultimate strength. Existing Table 3.2.3.0(j) has been revised to delete the T42 temper and the revision is designated Table 3.2.3.0(j₁) as illustrated in Table 11.

TABLE 1. TEST PLAN FOR 2024-142 EXTRUSIONS

Thickness, Inches	Grain Direction	Tensile	Compression	Shear	Bearing e/D = 1.5	Bearing e/D = 2/0
0.064	L	*	X	-	X	X
	LT	X	X	-	X	X
0.083	L	X	X	-	X	X
	LT	X	X	-	X	X
0.313	L	O**	O	O	O	O
	LT	O	O	O	O	O
0.430	L	X	X	X	X	X
	LT	X	X	X	X	X
0.500	L	X	X	X	X	X
	LT	X	X	X	X	X
1.000	L	O	O	O	O	O
	LT	O	O	O	O	O
1.250	L	O	O	O	O	O
	LT	O	O	O	O	O
1.500	L	O	O	O	O	O
	LT	O	O	O	O	O
1.700	L	O	O	O	O	O
	LT	O	O	O	O	O
1.750	L	O	O	O	O	O
	LT	O	O	O	O	O
2.000	L	O	O	O	O	O
	LT	O	O	O	O	O
2.562	L	X	X	X	X	X
	LT	X	X	X	X	X

* X-data available in reference (1).

** O-data to be obtained from testing.

TABLE 2. MECHANICAL PROPERTIES OF 2024-T42 EXTRUSIONS

Section Thickness, inches	Location	Gagein Direction	Tensile		Comp. Yield Strength, ksi	Shear Ultimate Strength, ksi	Bearing $e/D = 1.5$		Bearing $e/D = 2.0$	
			Ultimate Strength, ksi	Elongation, %			Ultimate Strength, ksi	Ultimate Strength, ksi	Ultimate Strength, ksi	Ultimate Strength, ksi
0.313	T/2, W/2	L	64.0	41.9	26.0	44.5	102.9	67.1	126.6	86.6
0.313	T/2	LT	67.3	42.7	14.0	45.3	-	-	-	-
1.000	T/2, W/4	L	67.5	42.7	24.0	45.8	102.9	71.1	128.7	84.7
1.000	T/2	LT	62.1	40.4	14.0	43.5	-	-	-	-
1.250	T/2, W/4	L	80.7	55.6	18.0	58.1	109.0	70.4	136.8	90.1
1.250	T/2	LT	70.1	46.5	20.0	49.7	-	-	-	-
1.500	T/2, W/4	L	82.2	57.3	18.0	59.3	107.9	69.7	139.1	86.0
1.500	T/2	LT	67.7	46.5	12.0	50.2	-	-	-	-
1.700	T/4, W/4	L	77.6	52.7	16.0	53.6	108.7	68.9	131.0	86.4
1.700	T/2	LT	63.5	45.2	8.0	48.8	-	-	-	-
1.750	T/4, W/4	L	79.2	55.0	14.0	57.6	104.7	66.4	128.7	86.7
1.750	T/2	LT	63.8	45.2	7.0	47.9	-	-	-	-
2.000	T/4, W/4	L	78.7	54.2	20.0	55.8	90.6	58.4	111.9	74.8
2.000	T/2	LT	63.7	43.3	6.0	46.2	-	-	-	-

TABLE 3. TENSILE, COMPRESSION, SHEAR, AND BEARING RATIOS FOR 2024-T42 EXTRUSIONS

Section Thickness, Inches	Location	$\frac{TUS(LT)}{TUS(L)}$	$\frac{TYS(LT)}{TYS(L)}$	$\frac{CVS(L)}{TYS(L)}$	$\frac{CVS(LT)}{TYS(L)}$	$\frac{SUS(L)}{TUS(L)}$	$\frac{SUS(LT)}{TUS(L)}$	$e/d = 1.5$		$e/d = 2.0$	
								$\frac{BUS(L)}{TUS(L)}$	$\frac{BYS(L)}{TYS(L)}$	$\frac{BUS(L)}{TUS(L)}$	$\frac{BYS(L)}{TYS(L)}$
0.313	T/2, W/2 T/2	1.052	1.019	1.067	1.081	0.705	0.653	1.608	1.601	1.978	2.067
1.000	T/2, W/4 T/2	0.920	0.946	1.073	1.019	0.636	0.604	1.524	1.665	1.907	1.984
1.250	T/2, W/4 T/2	0.869	0.836	1.045	0.894	0.533	0.542	1.351	1.266	1.695	1.621
1.500	T/2, W/4 T/2	0.824	0.806	1.028	0.870	0.504	0.523	1.313	1.208	1.692	1.490
1.700	T/4, W/4 T/2	0.818	0.858	1.017	0.926	0.528	0.523	1.401	1.307	1.688	1.639
1.750	T/4, W/4 T/2	0.806	0.822	1.047	0.871	0.514	0.516	1.322	1.207	1.625	1.576
2.000	T/4, W/4 T/2	0.809	0.799	1.030	0.852	0.537	0.529	1.151	1.077	1.422	1.380

TABLE 4. LIST OF RATIOS VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

	TUS(LT)/TUS(L)	TYS(LT)/TYS(L)	THICKNESS
1	1.063	.978	.064 (from ref. (1))
2	1.015	1.019	.083 (from ref. (1))
3	1.052	1.019	.313
4	.996	.990	.430 (from ref. (1))
5	.897	.872	.500 (from ref. (1))
6	.920	.946	1.000
7	.869	.836	1.250
8	.824	.806	1.500
9	.818	.858	1.700
10	.806	.822	1.750
11	.809	.799	2.000
12	.747	.774	2.562 (from ref. (1))

TABLE 4. CONTINUED

STATISTICS FOR THE PLOT OF TUS(LT)/TUS(L)
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.0367 - .1235 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .1072

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0358

R-SQUARED STATISTIC= 88.87

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON B(1) ARE 1.0046 AND 1.0687
 AND ON B(2) ARE -.1472 AND -.0997

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	1.006	.978
.500	.975	.951
.750	.944	.924
1.000	.913	.894
1.250	.882	.863
1.500	.851	.830
1.750	.821	.796
2.000	.790	.761
2.250	.759	.726
2.500	.728	.690
2.750	.697	.654
3.000	.666	.617

TABLE 4. CONCLUDED

STATISTICS FOR THE PLOT OF TYS(LT)/TYS(L)
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.0023 - .0995 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .0913

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0423

R-SQUARED STATISTIC= 78.57

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON B(1) ARE .9644 AND 1.0412

AND ON B(2) ARE -.1276 AND -.0725

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS MEAN RATIO REDUCED RATIO

.250	.977	.945
.500	.953	.925
.750	.928	.904
1.000	.903	.881
1.250	.878	.855
1.500	.853	.828
1.750	.828	.799
2.000	.803	.770
2.250	.778	.739
2.500	.754	.708
2.750	.729	.677
3.000	.704	.646

TABLE 5. LIST OF RATIOS VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

	CYS(L)/TYS(L)	CYS(LT)/TYS(L)	THICKNESS
1	1.007	1.067	.064 (from ref.(1))
2	1.058	1.055	.083 (from ref.(1))
3	1.062	1.081	.323
4	1.025	1.050	.430 (from ref.(1))
5	1.007	0.000	.500 (from ref.(1))
6	1.073	1.019	1.000
7	1.045	.894	1.250
8	1.028	.870	1.500
9	1.017	.826	1.700
10	1.047	.871	1.750
11	1.030	.852	2.000
12	.976	.814	2.562 (from ref.(1))

TABLE 5. CONTINUED

STATISTICS FOR THE PLOT OF CYS(L)/TYS(L)
VERSUS THICKNESS FOR
2024-T42 EXTRUSION

REGRESSED LINE IS
 $Y = 1.0446 - 0.0122 X$ (THICKNESS)

NUMBER OF DATA= 12

STANDARD DEVIATION OF $Y = .0275$

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE)= .0269

R-SQUARED STATISTIC= 4.73

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.
LIMITS ON B(1) ARE 1.0206 AND 1.0687
AND ON B(2) ARE -.0300 AND .0056

SIGNIFICANT REGRESSION NO

MEAN RATIO= 1.031

REVISED T STATISTIC= 1.796

REDUCED RATIO= 1.017

TABLE 5. CONCLUDED

STATISTICS FOR THE PLCT OF CYS(LT)/TYS(L)
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.0647 - .1132 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF Y = .1304

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0337

R-SQUARED STATISTIC= 86.75

95 PERCENT T FACTOR= 1.633

95 PERCENT CONF.

LIMITS ON $\bar{y}(1)$ ARE 1.0521 AND 1.1172
 AND ON $\bar{y}(2)$ ARE -.1365 AND -.0900

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SFLECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	1.056	1.028
.500	1.026	1.004
.750	1.000	.979
1.000	.971	.953
1.250	.943	.924
1.500	.915	.895
1.750	.887	.863
2.000	.858	.831
2.250	.830	.796
2.500	.802	.765
2.750	.773	.732
3.000	.745	.698

TABLE 6. LIST OF RATIOS VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

	SUS(L)/TUS(L)	SUS(LT)/TUS(L)	THICKNESS
1	.705	.653	.313
2	.536	.525	.430 (from ref.(1))
3	.494	.000	.500 (from ref.(1))
4	.636	.604	1.000
5	.533	.542	1.250
6	.504	.523	1.500
7	.528	.523	1.700
8	.514	.516	1.750
9	.537	.529	2.000
10	.476	.469	2.562 (from ref.(1))

TABLE 6. CONTINUED

STATISTICS FOR THE PLOT OF SUS(L)/TUS(L)
VERSUS THICKNESS FOR
2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = .6140 - .0521 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 10

STANDARD DEVIATION OF Y = .0763

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE)= .0623

R-SQUARED STATISTIC= 21.45

95 PERCENT T FACTOR= 1.860

95 PERCENT CONF.

LIMITS ON B(1) ARE .5370 AND .6910
AND ON B(2) ARE -.1041 AND .0000

SIGNIFICANT REGRESSION NO

MEAN RATIO= .546

REVISED T STATISTIC= 1.833

REDUCED RATIO= .506

TABLE 6. CONCLUDED

STATISTICS FOR THE PLOT OF SUS(LT)/TUS(L)
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = .620c - .0562 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 9

STANDARD DEVIATION OF Y = .0540

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0377

R-SQUARED STATISTIC= 51.29

95 PERCENT T FACTOR= 1.965

95 PERCENT CONF.

LIMITS ON B(1) ARE .5645 AND .6771
 AND ON B(2) ARE -.0926 AND -.6199

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	.667	.558
.500	.593	.552
.750	.579	.545
1.000	.565	.536
1.250	.551	.525
1.500	.536	.511
1.750	.522	.494
2.000	.508	.475
2.250	.494	.454
2.500	.480	.433
2.750	.466	.411
3.000	.452	.388

**TABLE 7. LIST OF RATIOS VERSUS THICKNESS FOR
 2024-T42 EXTRUSION**

	BUS(L)/TUS(L)1.5	BYS(L)/TYS(L)1.5	THICKNESS
1	1.597	1.692	.064 (from ref. (1))
2	1.489	1.779	.083 (from ref. (1))
3	1.608	1.601	.313
4	1.392	1.465	.430 (from ref. (1))
5	1.347	1.347	.500 (from ref. (1))
6	1.524	1.655	1.000
7	1.351	1.266	1.250
8	1.313	1.208	1.500
9	1.401	1.307	1.700
10	1.322	1.287	1.750
11	1.151	1.077	2.000
12	1.381	1.299	2.562 (from ref. (1))

TABLE 7. CONTINUED

STATISTICS FOR THE PLOT OF BUS(I)/TUS(I)1.5
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.5311 - .1200 X (\text{THICKNESS})$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .1335

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0942

R-SQUARED STATISTIC= 50.20

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON E(1) ARE 1.4467 AND 1.6155
 AND ON E(2) ARE -.1825 AND -.0574

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS MEAN RATIO REDUCED RATIO

.250	1.501	1.429
.500	1.471	1.409
.750	1.441	1.387
1.000	1.411	1.362
1.250	1.381	1.331
1.500	1.351	1.296
1.750	1.321	1.257
2.000	1.291	1.216
2.250	1.261	1.174
2.500	1.231	1.131
2.750	1.201	1.087
3.000	1.171	1.042

TABLE 7. CONCLUDED

STATISTICS FOR THE PLOT OF BYSIL/TYS(L11.5
 VEGUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.6446 - .2146 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .2258

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .1474

R-SQUARED STATISTIC= 57.37

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON B(1) ARE 1.5126 AND 1.7767
 AND ON B(2) ARE -.3124 AND -.1168

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	1.591	1.478
.500	1.537	1.441
.750	1.484	1.399
1.000	1.430	1.352
1.250	1.376	1.298
1.500	1.323	1.236
1.750	1.269	1.169
2.000	1.215	1.098
2.250	1.162	1.025
2.500	1.108	.951
2.750	1.054	.875
3.000	1.001	.799

TABLE 8. LIST OF RATIOS VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

	BUS(L)/TUS(L)2.0	BYS(L)/TYS(L)2.0	THICKNESS
1	1.894	1.953	.064 (from ref.(1))
2	1.644	2.106	.093 (from ref.(1))
3	1.973	2.067	.313
4	1.727	1.797	.430 (from ref.(1))
5	1.614	1.646	.500 (from ref.(1))
6	1.507	1.984	1.000
7	1.695	1.621	1.250
8	1.632	1.490	1.500
9	1.693	1.639	1.700
10	1.625	1.576	1.750
11	1.422	1.380	2.000
12	1.639	1.569	2.552 (from ref.(1))

TABLE 8. CONTINUED

STATISTICS FOR THE PLOT OF BUS(L)/TUS(L)2.0
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.9547 + .1264 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .1545

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .1198

R-SQUARED STATISTIC= 39.91

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON B(1) ARE 1.7574 AND 1.9720
 AND ON B(2) ARE -.2059 AND -.0469

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	1.833	1.741
.500	1.802	1.723
.750	1.770	1.701
1.000	1.738	1.675
1.250	1.707	1.643
1.500	1.675	1.605
1.750	1.643	1.562
2.000	1.612	1.517
2.250	1.580	1.469
2.500	1.549	1.421
2.750	1.517	1.371
3.000	1.485	1.322

TABLE 8. CONCLUDED

STATISTICS FOR THE PLOT OF BYE(L)/TYS(L)2.0
 VERSUS THICKNESS FOR
 2024-T42 EXTRUSION

REGRESSED LINE IS

$$Y = 1.9978 + .2388 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 12

STANDARD DEVIATION OF Y = .2394

STANDARD ERROR OF ESTIMATE

(OR EFFECTIVE SCATTER ABOUT THE LINE)= .1535

R-SQUARED STATISTIC= 58.89

95 PERCENT T FACTOR= 1.812

95 PERCENT CONF.

LIMITS ON B(1) ARE 1.8503 AND 2.1253
 AND ON B(2) ARE -.3319 AND -.1282

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS	MEAN RATIO	REDUCED RATIO
.250	1.930	1.813
.500	1.873	1.772
.750	1.815	1.728
1.000	1.758	1.677
1.250	1.700	1.618
1.500	1.643	1.557
1.750	1.585	1.481
2.000	1.528	1.406
2.250	1.470	1.328
2.500	1.413	1.249
2.750	1.355	1.169
3.000	1.296	1.088

TABLE 9. COMPUTED REDUCED RATIOS* FOR 2024-T47 EXTRUSIONS

Property Ratio	Ratio	Thickness, inches											
		<u>≤0.249</u>	<u>0.250-0.499</u>	<u>0.500-0.749</u>	<u>0.750-0.999</u>	<u>1.000-1.249</u>	<u>1.250-1.499</u>	<u>1.500-1.749</u>	<u>1.750-1.999</u>	<u>2.000-2.249</u>	<u>2.250-2.499</u>		
TUS (LT) / TUS (L)	--	<u>0.978</u>	<u>0.951</u>	<u>0.925</u>	<u>0.894</u>	<u>0.863</u>	<u>0.830</u>	<u>0.796</u>	<u>0.761</u>	<u>0.726</u>	<u>0.690</u>		
TYS (LT) / TYS (L)	--	<u>0.945</u>	<u>0.925</u>	<u>0.904</u>	<u>0.881</u>	<u>0.855</u>	<u>0.828</u>	<u>0.799</u>	<u>0.770</u>	<u>0.739</u>	<u>0.708</u>		
CYS (L) / TYS (L)	--	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>	<u>1.017</u>		
CYS (LT) / TYS (L)	--	<u>1.028</u>	<u>1.004</u>	<u>0.979</u>	<u>0.953</u>	<u>0.924</u>	<u>0.895</u>	<u>0.863</u>	<u>0.831</u>	<u>0.798</u>	<u>0.765</u>		
SUS (L) / TUS (L)	--	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>	<u>0.506</u>		
SUS (LT) / TUS (L)	--	<u>0.558</u>	<u>0.552</u>	<u>0.545</u>	<u>0.536</u>	<u>0.525</u>	<u>0.511</u>	<u>0.494</u>	<u>0.475</u>	<u>0.454</u>	<u>0.433</u>		
BUS (L) / TUS (L)	1.5	<u>1.429</u>	<u>1.409</u>	<u>1.387</u>	<u>1.362</u>	<u>1.331</u>	<u>1.296</u>	<u>1.257</u>	<u>1.216</u>	<u>1.174</u>	<u>1.131</u>		
BYS (L) / TYS (L)	1.5	<u>1.478</u>	<u>1.441</u>	<u>1.399</u>	<u>1.352</u>	<u>1.298</u>	<u>1.236</u>	<u>1.169</u>	<u>1.098</u>	<u>1.025</u>	<u>0.951</u>		
BUS (L) / TUS (L)	2.0	<u>1.741</u>	<u>1.723</u>	<u>1.702</u>	<u>1.675</u>	<u>1.643</u>	<u>1.605</u>	<u>1.562</u>	<u>1.517</u>	<u>1.469</u>	<u>1.421</u>		
BYS (L) / TYS (L)	2.0	<u>1.813</u>	<u>1.772</u>	<u>1.72</u>	<u>1.677</u>	<u>1.618</u>	<u>1.553</u>	<u>1.481</u>	<u>1.406</u>	<u>1.328</u>	<u>1.249</u>		

* Underlined ratios used to compute design values.

TABLE 10. PROPOSED MIL-HDBK-5 TABLE 3.2.3.0(1)
 TABLE 3.2.3.0(1). Design Mechanical and Physical Properties of
 2024 Aluminum Alloy (Extrusions) - Continued

Specification	QQ-A-200/3									
Form	Extruded, bars, rods, and shapes									
Condition	T42 ^a									
Cross-sectional area, in. ²	<25									
Thickness or diameter, in.	0.249-0.499	0.250-0.749	0.500-0.999	0.750-1.249	1.000-1.499	1.250-1.749	1.500-1.999	1.750-2.249	2.000-2.499	2.250-2.499
Basis	S	S	S	S	S	S	z	S	S	S
Properties:										
F_{tu}^a, ksi:										
L	57	57	57	57	57	57	57	57	57	57
LT	55	54	52	51	49	47	45	43	41	39
F_{cy}^a, ksi:										
L	38	38	38	38	38	38	38	38	38	38
LT	36	35	34	33	32	31	30	29	28	27
F_{cy}^a, ksi:										
L	38	38	38	38	38	38	38	38	38	38
LT	39	38	37	36	35	34	33	31	30	29
F_{su}^a, ksi										
.....	29	29	29	29	29	29	28	27	26	24
F_{bru}^b, ksi:										
(e/D = 1.5)	81	80	79	77	76	74	71	69	67	64
(e/D = 2.0)	99	98	97	95	93	91	89	86	83	81
F_{try}^b, ksi:										
(e/D = 1.5)	56	55	53	51	49	47	44	41	39	36
e/D = 2.0)	69	67	65	63	61	59	56	53	50	47
e, percent:										
L	12	12	12	10	10	10	10	10	10	10
LT
E, 10³ ksi										
10.8										
E_c, 10³ ksi										
11.0										
G_c, 10³ ksi										
4.1										
ν										
0.33										
C, K, and α										
See Figure 3.2.3.0.										

^a These allowables apply when samples of material supplied in the O or F temper are heat treated to demonstrate response to heat treatment. Properties obtained by the user however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.


^b Bearing values are "dry pin" values per Section 1.4.7.1.

TABLE 11. PROPOSED MIL-HDBK-5 TABLE 3.2.3.0(J₁)
 TABLE 3.2.3.0(J₁). Design Mechanical and Physical Properties of 2024 Aluminum Alloy (Extrusions)

Specification Form Temper	2024 T300/A																	
	1 standard bars, rods, and shapes																	
	4, T3510 and T3511						18, T8310 and T8311											
	<0.249		0.250-0.499		0.500-1.499		1.500-2.999		3.000-4.999		5.000-15.000							
Thickness, in.	A	B	A	B	A	B	A	B	A	B	A	B	<0.249	0.250-0.499	0.500-1.499	1.500-2.999	3.000-4.999	5.000-15.000
Cross-sectional area, in. ²	A	B	A	B	A	B	A	B	A	B	A	B	<25	>25, <32	>32	<20	<37	>37
Mechanical properties	A	B	A	B	A	B	A	B	A	B	A	B	<20	>25, <32	>32	<20	<37	>37
F_{up} , ksi	57	61	60	62	60	62	65	70	70	74	70	74	68	68	68	64	66	66
F_{L}	54	58	56	57	54	56	56	60	55	58	54	57	51	52	52	64	64	61
F_{T} , ksi	42	47	44	47	44	47	46	54	52	54	52	54	48	48	48	56	58	58
F_{L}	37	41	38	40	37	39	37	43	39	41	39	41	36	36	36	55	57	57
F_{T} , ksi	34	38	37	39	38	40	41	48	49	50	49	51	45	45	45	57	59	59
F_{L}	41	45	43	44	40	43	40	47	42	44	41	43	38	38	38	57	59	59
F_{T} , ksi	29	31	31	32	30	31	31	35	34	36	33	35	32	32	32	35	36	36
$F_{B0.2}$, ksi	84	90	78	81	78	80	84	90	88	93	86	91	84	84	84	94	96	92
σ (E/D=1.5)	108	114	98	101	97	101	105	113	111	118	109	115	108	106	106	123	123	117
σ (E/D=2.0)	61	68	55	59	55	59	57	63	66	62	65	65	57	57	57	79	82	82
σ (E/D=2.0)	71	79	67	71	67	71	69	81	77	80	75	78	71	69	69	93	96	96
σ_c , percent (S usasipt)	12	12	12	12	10	10	10	10	10	10	10	10	8	8	8	4	5	5
L_T	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60
E , 10 ⁶ ksi	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
E_c , 10 ⁶ ksi	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
G , 10 ⁶ ksi	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1
μ	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31	0.31
α , 10 ⁻⁶ /in. ³	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
C, K and σ	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8


See Figure 1.2.1.10

*Bearing values are "dry pin" values per Section 1.4.7.1



TYPE	L	G	F	D	THREAD
1	2"	5/8"	11/16"	1/2"	1/2 - 13 NC
2	2 1/4"	5/8"	13/16"	1/2"	1/2 - 13 NC
3	2 1/2"	5/8"	15/16"	1/2"	1/2 - 13 NC
4	2 1/2"	5/8"	15/16"	3/8"	3/8 - 16 NC
A-1209	3"	1 1/4"	7/8"	1/2"	1/2 - 13 NC

Figure 1. Tensile Specimen



Note. Ends to be flat and parallel to within
00002" of centerline

TYPE	L	D
1	1 1/2"	.500"
2	1"	.313"

Figure 2. Compression Specimen





Figure 3. Shear Specimen



TYPE	W	$\frac{e}{D} = 1.5$	$\frac{e}{D} = 2.0$	t
1	1"	.375	.500	.063"
2	1 1/8"	.375	.500	.074"
3	1 1/4"	.375	.500	.074"
4	1 1/2"	.375	.500	.074"

Figure 4. Bearing Specimen




Figure 5. Location of Long Transverse Specimens
 For 1" x 2-1/2" Bar




Figure 6. Location of Longitudinal Specimens
 For 1" x 2-1/2" Bar




Figure 7. Location of Transverse Specimens
 For $1\frac{1}{4}$ " x $2\frac{1}{4}$ " Bar




Figure 8. Location of Longitudinal Specimens
 For $1\frac{1}{4}$ " x $2\frac{1}{4}$ " Bar




Figure 9. Location of Long Transverse Specimens
For 1-1/2" x 2-1/2" Bar




Figure 10. Location of Longitudinal Specimens
For 1-1/2" x 2-1/2" Bar




Figure 11. Location of Long Transverse Specimens
For 2" x 2" Bar




Figure 12. Location of Longitudinal Specimens
For 2" x 2" Bar




Figure 13. Location of Long Transverse Specimens
For 1-3/4" x 3" Bar




Figure 14. Location of Longitudinal Specimens
For 1-3/4" x 3" Bar




Figure 15. Location of Longitudinal Specimens For Angle




Figure 16. Location of Long Transverse Specimens For Angle




Figure 17. Location of Longitudinal Specimens For Zee




Figure 18. Location of Long Transverse Specimens For Zee




Figure 19. Plot of TUS (LT)/TUS (L) Ratios




Figure 20. Plot of TYS (LT)/TYS (L) Ratios




Figure 21. Plot of CYS (L)/TYS (L) Ratios




Figure 22. Plot of CYS (LT)/TYS (L) Ratios




Figure 23. Plot of SUS (L)/TUS (L) Ratios




Figure 24. Plot of SUS (LT)/TUS (L) Ratios




Figure 25. Plot of BUS (L)/TUS (L), $e/d = 1.5$, Ratios




Figure 26. Plot of $BYS(L)/TYS(L)$, $e/D = 1.5$, Ratios




Figure 27. Plots of BUS (L)/TUS (L), $e/D = 2.0$, Ratios




Figure 28. Plot of BY5 (L)/TYS (L), $e/D = 2.0$, Ratios

Ti-6Al-2Sn-4Zr-2Mo Titanium Alloy Sheet

Background

MIL-HDBK-5 currently contains in Table 5.3.3.0(b) A and B values for tensile yield and ultimate strengths for Ti-6Al-2Sn-4Zr-2Mo duplex annealed sheet, but does not have compression, shear, and bearing data. This material is being considered for use in several advanced aircraft and missiles in elevated temperature applications. Consequently, it was desirable to establish the missing design properties for this material.

A literature search revealed that room and elevated temperature tensile, compression, shear, and bearing data for Ti-6Al-2Sn-4Zr-2Mo duplex annealed sheet were available in reference (2). Since the data contained in this reference were insufficient to meet the MIL-HDBK-5 guideline requirements, it was necessary to conduct a test program to resolve this matter.

Test Plan. As defined in Chapter 1, Section 1.4.3 of MIL-HDBK-5, derived values are those room temperature mechanical property values that are established through their relationship to directly calculated (or specification) values for room temperature F_{tu} and F_{ty} . The guidelines for the presentation of data are described in Chapter 9, Section 9.2.9.1, of MIL-HDBK-5 and require at least ten pairs of measurements, each representing a single lot of material. Table 1 shows the test plan to acquire the necessary data. Although data were available from reference (2) for one lot of material, it was decided to procure ten lots of material because the test material in reference (2) had been produced over 14 years ago and the silicon content was not known. MIL-HDBK-5 contains elevated temperature tensile yield and ultimate strength data. It was decided to perform testing so that elevated temperature compression yield and shear ultimate strength data could be included in MIL-HDBK-5. The test plan was designed so as to utilize test material which could be procured immediately.

Material. Rockwell International Corporation, Military Aircraft Division (Columbus, Ohio) supplied at no cost five lots of material in 0.071, 0.080, 0.090, 0.100, and 0.125-inch thicknesses. This material had been produced by RMI to a Rockwell specification, which was equivalent to MIL-T-9046 except requiring a silicon content of 0.06-0.10 percent. Five additional sheet thicknesses; 0.030, 0.040, 0.050, 0.055 and 0.062, were procured from TIMET to MIL-T-9046, Type III, Comp. 6, except silicon content was specified as 0.06-0.10 percent. Each sheet thickness constituted a different heat except for 0.055 and 0.063-inch thicknesses which were from the same heat.

(2) Dotson, C.L., "Mechanica' and T Properties of High-Temperature Titanium Alloys", Source: AFML-TR-67-41 (April 1967), (MCIC 68426).

The material was supplied in the duplex annealed condition. This thermal treatment consisted of 1650 F for 1/2-hour, air cool, 1450 F for 1-4/4hour and air cool.

Test Specimens. Triplicate tests were used as shown in Table 12. The configurations of the test specimens are shown in Figures 29 through 32. The location of the test specimens on the sheet is depicted in Figures 33 through 37.

Testing. All specimens were tested in the "as received" duplex annealed condition in accordance with the procedures described in Appendix A. The results of the mechanical property tests are shown in Table 13. All lots conformed to the minimum tensile properties specified in MIL-T-9046.

Great difficulty was experienced with the shear testing. All of planned shear specimens had long transverse grain orientation. The first specimen tested was A1 (0.030-inch) thick. Severe deformation occurred around test holes (see Figure 31 for specimen configuration) and examination of fracture surfaces revealed that the fracture was not totally by shear. A thicker specimen, GT1 (0.080-inch thick) was tested next to determine if the problem would prevail in thicker specimens. Again, severe deformation in test area was observed with circuitous cracks between the test holes. To further determine whether thickness of specimen was a factor, specimen JT1 (0.125-inch thick) was tested with similar results.

There are no published specifications for shear testing and test specimen configuration. The shear specimen configuration shown in Figure 3 has been used successfully for a large number of different metallic materials over an extended period of time. Problems in obtaining a shear failure have only been encountered in the past with materials with a very low yield strength (30-50 Ksi). Reducing the width between the test holes has been effective in the past in producing shear failures in low yield strength materials.

Consequently, the width between the test holes on specimen GT2 (0.080-inch thick) was reduced from 0.190 to 0.150-inch by machining, but this change did not produce a shear failure. The same procedure was used on specimen JT2 (0.125-inch thick) without success. The width between the test holes on specimen HT1 (0.090-inch thick) was reduced to 0.100-inch; on specimens ET1 (0.063-inch thick) and GT3 (0.080-inch thick), the test width was reduced to 0.075-inch, but none of these modifications produced a shear failure.

It was thought that possibly shear failures could be obtained with longitudinal specimens. Longitudinal specimens were machined from 0.100-inch thick sheet with test widths of 0.124 and 0.248-inch and tested without success. On the third specimen, the original 0.190-inch test width was reduced to 0.120-inch using a jeweler's saw with 0.006-inch diameter blade in an effort to increase

the stress concentration at the test section. This was unsuccessful. On the fourth longitudinal specimen, the 0.190-inch test width was reduced to 0.100-inch by electrical discharge machining (0.014-inch wide slot). Since this technique did not produce a shear failure, shear testing was discontinued.

Analysis. As previously indicated, derived values refer to those room temperature mechanical property values that are established through their relationships to directly calculated (or specification) values for room temperature F_{TU} and F_{TY} . The procedure is applicable to F_{CY} , F_{SU} , F_{BRU} , and F_{BY} and involves the pairing of SUS and EIS measurements with TUS measurements for which F_{TU} has been established. Likewise, CYS and BYS measurements are paired with TYS measurements for which F_{TY} has been established. Tensile properties in grain directions not covered by specification are also derived in a similar manner.

Using the above relationships, reduced ratios for the various "unknown" properties were determined using the computational procedure described in Chapter 9, Section 9.2.9.2 of MIL-HDBK-5. The primary test direction for sheet is long transverse. Consequently, the lot average test values for longitudinal and long transverse compression yield and long transverse bearing yield strength were paired with the corresponding lot average test values for long transverse tensile yield strength. Similarly, the long transverse bearing ultimate values were paired to the corresponding long transverse tensile ultimate values. Reduced ratios were computed using the following equation when the ratios did not vary with thickness:

$$R = \bar{r} - \frac{t_{0.95^s}}{\sqrt{n}}$$

where P = reduced ratio

\bar{r} = average of n ratios

s = standard deviation of the ratios

$t_{0.95}$ = the 0.95 fractile of the t distribution corresponding to $n-1$ degrees of freedom

n = number of ratios.

When the ratio varied with thickness, the following equation was used for regression analysis:

$$R = \bar{r}' - t_{0.95^s} \sqrt{\frac{1}{n} + \frac{(x_0 - \sum x/n)^2}{(\sum x^2) - (\sum x)^2/n}}$$

- where
- R = reduced ratio
 - \bar{r} = mean ratio for specific thickness, x_0
 - s' = standard error of estimate
 - $t_{0.95}$ = the 0.95 fractile of the t distribution corresponding to n-2 degrees of freedom
 - n = number of ratios
 - x_0 = specific thickness
 - x = individual thickness values for ratios.

A computer program was used to perform the analyses. The results are shown in Tables 14 through 16.

Only the $\frac{BUS}{TUS}$ ratios showed regression (positive) with increasing thickness as shown in Table 16, and Figures 38 and 39. Because of this regression for the $\frac{BUS}{TUS}$ ratios, it was decided to present design values for four thickness ranges for sheet. A summary of the computed reduced ratios is presented in Table 17.

MIL-HDBK-5 Table 5.3.3.0(b) does not contain a compression modulus value for Ti-6Al-2Sn-4Zr-2Mo sheet. Consequently, an E_c value was determined by using the same ratio technique. This computed average ratio for $\frac{E_c}{E}$ is shown in Table 18. Since moduli are presented as typical values, not minimum, the average ratio was used to compute E_c value.

The same equation (not regression) that was used to compute a lower confidence interval (reduced ratio) for compression yield and bearing yield strengths was utilized to compute the lower confidence intervals at each test temperature for compression yield strength. The results of these computations are shown in Table 19.

The effect of temperature on compressive modulus was established by the computations in Table 20. Since the elevated temperature moduli curves in MIL-HDBK-5 are typical, not minimum, the average percentage of room temperature value at each temperature was used.

The reduced ratios in Tables 17 and 18 were used to compute design values in revised Table 5.3.3.0(b) (Table 21) for compression and bearing strength as well as compression modulus value. The compression yield strength lower confidence interval at each temperature was used to construct elevated temperature working curve in Figure 40. The corresponding MIL-HDBK-5 illustration is shown in Figure 41. The elevated temperature compression modulus curve was determined using average percentages shown in Table 20. These percentages were plotted on the existing MIL-HDBK-5 Figure 5.3.3.1.4 for comparison with the elevated temperature tensile modulus curve as depicted in Figure 42. The elevated temperature percentages for compression modulus compared closely with those for tensile modulus. Consequently, the caption for the existing Figure 5.3.3.1.4 has been changed as shown in Figure 43.

TABLE 12. TISI PLAN FOR 11-6Al-28Ni-4Zr-2Mo SHEET

Sheet Thickness	Grain Direction	Room Temperature				Elevated Temperature, 400 F., 800 F., 1000 F.		
		Tensile	Compression	Shear	Bearing $r/D=1.5$	Bearing $r/d=2.0$	Compression	Shear
0.010	L	3		3	3			
	LT							
0.040	L	3		3	3			
	LT							
0.050	L	3		3	3		3	3
	LT							
0.055	L	3		3	3			
	LT							
0.063	L	3		3	3			
	LT							
0.071	L	3		3	3			
	LT							
0.080	L	3		3	3		3	3
	LT							
0.090	L	3		3	3			
	LT							
0.100	L	3		3	3			
	LT							
0.125	L	3		3	3		3	3
	LT							
0.040*	L	X	X	X	X	X	X	X
	LT	X	X	X	X	X	X	X

*Data available in reference (2).

TABLE 13. MECHANICAL PROPERTIES OF T1-6AL-2SN-4ZR-2MO SHEET

Inot Number	Thickness, Inches	Temperature, °F	Grain Direction	Specimen Identification	Tension			Compression		Bending			
					TUS, ksi	TS, ksi	e, percent in 2 in.	% Elong. 10-ksi	CS, ksi	% Elong. 10-ksi	BIS, ksi	BIS, ksi	RIS, ksi
N-0082	0.030	RT	L	A11	133.3	143.1	16.0	156.9	18.5	217.1	195.4	243.1	239.8
				A12	150.5	161.0	13.0	153.5	18.8	236.2	204.1	243.0	226.2
				A13	151.3	163.2	12.5	156.9	18.5	202.2	193.0	240.4	197.3
				Average	151.7	163.4	13.2	156.6	18.6	217.8	197.5	262.8	217.8
				B12	160.5	19.2	19.2	160.5	19.2				
				B13	160.6	19.2	19.2	160.6	19.2				
N-6117	0.040	RT	L	Average	148.3	146.7	17.4	161.2	19.2	232.9	193.9	281.3	261.3
				W2	168.4	130.1	12.5	150.1	10.2	230.6	191.3	261.7	235.6
				RT3	149.6	141.5	17.0	150.4	18.3	239.8	192.3	248.0	217.9
				Average	162.1	140.1	12.0	149.2	10.2	231.1	192.5	263.7	238.3
				C11	153.9	19.1	19.1	153.9	19.1				
				C13	156.7	19.2	19.2	156.7	19.2				
P-7109	0.050	RT	L	Average	137.4	143.1	15.0	156.0	18.6	241.7	199.3	298.0	330.0
				G12	151.3	162.2	16.0	157.3	10.4	233.2	192.0	277.1	230.2
				G13	151.3	162.2	17.5	152.7	10.5	234.0	196.8	276.5	231.2
				Average	151.3	162.2	16.2	157.0	10.7	236.3	196.8	276.5	231.2
				G16	141.4	18.0	18.0	141.4	18.0				
				G18	146.7	17.7	17.7	146.7	17.7				
P-7109	600	RT	L	Average	117.6	116.3	11.6	117.6	11.6				
				G17	101.9	16.9	16.9	101.9	16.9				
				G18	101.9	16.4	16.4	101.9	16.4				
				Average	101.9	16.4	16.4	101.9	16.4				
				G19	101.9	16.4	16.4	101.9	16.4				
				Average	101.9	16.4	16.4	101.9	16.4				

TABLE 13. CONTINUED

Inlet through	Thickness, Inches	Tempera- ture F.	Grain Direction	Specimen Identifi- cation	Tension			Compression			Biaxial					
					T ₁₀ , ksi	T ₅₀ , ksi	% elong.	C ₁₀ , ksi	C ₅₀ , ksi	% short.	σ_1/σ_2 , ksi	σ_1/σ_2 , ksi	σ_1/σ_2 , ksi			
P-7109	0.050	800	LT	CT10				98.6	15.6							
				CT11				70.4	15.6							
				CT17				70.1	15.7							
				Average (CT11)				70.4	15.7							
				CT15				88.9	16.6							
P-6426	0.055	RT	L	Average				166.0	18.1							
				BI 1				166.6	18.1							
				BI 2				166.3	18.0							
				BI 3				166.2	18.1							
				Average				166.7	18.1							
P-6426	0.061	RT	LT	BT1	162.6	167.6	16.5	160.6	19.4	17.1	216.2	194.0	274.7	236.6		
				BT2	150.4	161.0	16.0	160.6	19.5	17.1	216.4	190.2	270.4	238.5		
				BT3	168.4	161.8	13.3	160.7	19.5	17.2	216.4	190.2	270.4	238.5		
				Average	162.5	163.7	16.0	160.7	19.6	17.2	216.2	191.6	270.4	239.6		
				BI 1				163.5	18.5							
80070 T-03-2	0.071	RT	L	BI 2	168.5	167.5	15.0	166.5	18.3	17.0	232.0	186.3	294.8	237.8		
				BI 3				156.3	19.3	17.3	237.8	195.5	297.3	239.8		
				Average	168.9	167.4	16.0	156.7	19.3	17.3	237.8	195.5	297.3	239.8		
				BT1	160.1	162.8	15.0	157.6	19.2	16.7	236.9	196.5	293.8	241.9		
				Average	160.8	162.5	16.7	156.8	19.3	17.3	236.6	195.4	295.3	239.8		
80070 T-03-2	0.071	RT	LT	BI 1	155.7	163.1	16.0	155.3	18.3	15.5	226.5	189.7	292.5	233.2		
				BI 2				155.2	18.6	16.6	229.4	197.0	294.2	230.2		
				BI 3				166.7	16.6	17.6	230.8	193.4	295.2	232.0		
				Average	166.1	163.4	16.7	168.7	17.6	15.8	228.9	191.7	294.0	231.8		
				BT1				168.7	17.6	15.8	228.9	191.7	294.0	231.8		

TABLE 13. CONTINUED

Heat Number	Thickness, Inches	Tempera- ture, F.	Grain Direction	Specimen Location and Orientation	Tension			Compression		Bearing		
					TUG, kcal	% in 2 in.	$\frac{F}{10}$, kcal	CVS, kcal	$\frac{F}{10}$, kcal	$\frac{e/D=1.3}{RIS}$, kcal	$\frac{e/D=2.0}{RIS}$, kcal	$\frac{e/D=2.0}{RIS}$, kcal
R90462-13-5	0.080	RT	L	G13			159.1	18.4				
				G17			159.5	18.7				
				Average			160.3	18.7				
		LT	G21	151.4	16.7	159.6	18.6	238.6	280.9	303.9	233.4	
			G22	150.7	16.5	159.6	18.6	237.8	280.9	304.1	237.2	
			Average	150.6	16.3	159.6	18.6	237.0	280.4	306.3	237.0	
600	LT	G24	153.2	16.8	153.2	16.8	113.2	16.8				
		G25	113.5	17.0	113.5	17.0						
		Average	113.6	16.9	113.6	16.9						
600	LT	G26	104.3	15.9	104.3	15.9						
		G27	104.2	15.8	104.2	15.8						
		Average	104.3	15.9	104.3	15.9						
800	LT	G10	91.9	14.9	91.9	14.9						
		G11	91.4	14.7	91.4	14.7						
		Average	91.7	14.8	91.7	14.8						
1000	LT	G14	85.7	13.0	85.7	13.0						
		G15	85.5	13.1	85.5	13.1						
		Average	85.6	13.0	85.6	13.0						
R90462-04-4	0.090	RT	L	H11	146.7	14.0	154.8	18.5	242.9	198.0	103.4	233.6
				H12	146.9	13.5	153.7	18.6	243.7	202.0	308.3	237.7
				Average	146.8	13.8	154.3	18.7	240.5	199.9	307.3	237.0
800	LT	H13	146.1	14.0	153.9	18.6	242.4	200.2	307.0	232.0		
		Average	146.1	14.0	153.9	18.6	242.4	200.2	307.0	232.0		

TABLE 13. CONCLUDED

Heat Number	Thickness, Inches	Temperature, °F	Grain Direction	Specimen Identification	Tension			Compression			Reaction			
					TUS, Kcal	TYS, Kcal	% Elongation in 2 In.	CYS, Kcal	10-Kcal	10-Kcal	BUS, Kcal	BYS, Kcal	BUS, Kcal	BYS, Kcal
Ann 70-10-1	0.100	RT	L	J11				154.3	19.2					
				J12				152.3	19.2					
				J13				152.9	19.3					
				Average				153.2	19.2					
				J17	145.8	146.8	13.5	150.0	18.7		238.6	199.3	300.6	235.1
			LT	J12	165.6	160.1	15.0	151.2	18.7		738.1	195.3	299.6	235.1
				J13	166.0	160.3	16.0	151.5	18.8		240.5	197.8	299.6	239.1
				Average	165.8	160.4	15.2	150.9	18.7		239.1	197.6	299.2	239.5
				J14				151.9	18.7					
				J15				152.6	19.0					
Ann 70-10-1	0.125	400	L	Average	155.7	143.3	16.0	152.3	18.9		738.6	197.3	299.8	239.8
				J12	165.8	161.3	16.5	150.7	18.6		239.4	200.5	300.6	240.6
				J13	166.1	161.9	15.0	150.6	18.6		-	201.1	302.9	236.2
				Average	165.8	161.8	15.2	150.4	18.5		239.0	199.5	301.1	239.5
				J14				113.9	17.7					
			LT	J15				113.6	17.2					
				J16				113.9	17.2					
				Average				113.0	17.2					
				J17				101.4	16.4					
				J18				101.2	16.2					
Ann 70-10-1	0.125	600	LT	J18				100.9	16.1					
				J19				101.2	16.2					
				Average				97.5	15.1					
				J110				95.1	14.0					
				J111				95.1	15.6					
			LT	J112				95.2	15.2					
				J113				81.9	13.4					
				Average				81.3	13.8					
				J114				81.0	14.1					
				J115				81.4	13.8					

TABLE 14. LIST OF RATIOS VERSUS THICKNESS FOR
 TI-6AL-2SN-4ZR-2MO

	CYS(L)/TYS(LT)	CYS(LT)/TYS(LT)	THICKNESS
1	1.105	1.077	.038
2	1.151	1.069	.040 (from ref. (2))
3	1.075	1.038	.040
4	1.099	1.076	.050
5	1.018	1.132	.055
6	1.025	1.100	.063
7	1.082	1.037	.071
8	1.098	1.061	.080
9	1.086	1.079	.090
10	1.091	1.075	.100
11	1.074	1.061	.125

TABLE 14. CONTINUED

STATISTICS FOR THE PLOT OF CYS(L)/TYS(LT)
VERSUS THICKNESS FOR
TI-6AL-2SN-4ZR-2MO

REGRESSED LINE IS

$$Y = 1.0957 - .1998 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF Y = .0366

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE)= .0381

R-SQUARED STATISTIC= .831

95 PERCENT T FACTOR= 1.833

95 PERCENT CONF.

LIMITS ON B(1) ARE 1.0402 AND 1.1512
AND ON B(2) ARE -.9597 AND .5601

SIGNIFICANT REGRESSION NO

MEAN RATIO= 1.082

REVISED T STATISTIC= 1.812

REDUCED RATIO= 1.062

TABLE 14. CONCLUDED

STATISTICS FOR THE PLOT OF CYS(LT)/TYS(LT)
VERSUS THICKNESS FOR
TI-6AL-2SN-4ZR-2MO

REGRESSED LINE IS

$$Y = 1.0792 - .0695 X (\text{THICKNESS})$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF Y = .0266

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE) = .0280

R-SQUARED STATISTIC= *****

95 PERCENT T FACTOR= 1.833

95 PERCENT CONF.
LIMITS ON B(1) ARE 1.0385 AND 1.1200
AND ON B(2) ARE -.6473 AND .4685

SIGNIFICANT REGRESSION NO

MEAN RATIO= 1.073

REVISED T STATISTIC= 1.812

REDUCED RATIO= 1.059

TABLE 15. LIST OF RATIOS VERSUS THICKNESS FOR
 TI-6AL-2SN-4ZR-2MO

	BYS (LT)/TYS (LT) 1.5	BYS (LT)/TYS (LT) 2.0	THICKNESS
1	1.377	1.519	.030
2	1.374	1.701	.040 (from ref (2))
3	1.428	1.701	.040
4	1.384	1.6	.050
5	1.352	1.6	.055
6	1.371	1.63	.063
7	1.337	1.616	.071
8	1.380	1.616	.080
9	1.404	1.633	.090
10	1.407	1.684	.100
11	1.407	1.689	.125

TABLE 15. CONTINUED

STATISTICS FOR THE PLOT OF $\text{EYS(ILT)}/\text{TYS(LT)15}$
VERSUS THICKNESS FOR
7I-6A1-25N-4ZF-2M0

REGRESSED LINE IS

$$Y = 1.3670 - .2479 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF $Y = .0264$

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE)= .0266

R-SQUARED STATISTIC= .2,83

95 PERCENT T FACTOR= 1.837

95 PERCENT CONF.

LIMITS ON $B(1)$ ARE 1.3279 AND 1.4066
AND ON $B(2)$ ARE -.2859 AND .7817

SIGNIFICANT REGRESSION NO

MEAN RATIO= 1.364

REVISED T STATISTIC= 1.812

REDUCED RATIO= 1.369

TABLE 15. CONCLUDED

STATISTICS FOR THE PLOT OF $BYS(LT)/TYS(LT)2.0$
 VERSUS THICKNESS FOR
 TI-6AL-2SN-4ZR-2MO

REGRESSED LINE IS

$$Y = 1.6183 + .4853 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF Y = .0562

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE)= .0574

R-SQUARED STATISTIC= -4.04

95 PERCENT T FACTOR= 1.833

95 PERCENT CONF.

LIMITS ON $B(1)$ ARE 1.5347 AND 1.7020
 AND ON $B(2)$ ARE -0.6561 AND 1.6327

SIGNIFICANT REGRESSION NO

MEAN RATIO= 1.651

REVISED T STATISTIC= 1.812

REDUCED RATIO= 1.621

TABLE 16. LIST OF RATIOS VERSUS THICKNESS FOR
 TI-6AL-2SN-4ZR-2MO

	BUS(LT)/TUS(LT) 1.5	BUS(LT)/TUS(LT) 2.0	THICKNESS
1	1.436	1.601	.030
2	1.550	1.769	.040 (from ref (2))
3	1.607	1.993	.040
4	1.562	1.960	.050
5	1.571	1.902	.055
6	1.590	1.965	.063
7	1.567	2.012	.071
8	1.579	2.028	.080
9	1.659	2.161	.090
10	1.640	2.057	.100
11	1.639	2.065	.125

TABLE 16. CONTINUED

STATISTICS FOR THE PLOT OF BUS(LT)/TUS(LT)15
 VERSUS THICKNESS FOR
 TI-6AL-2SN-4ZR-2MO

REGRESSED LINE IS

$$Y = 1.4782 + 1.5316 X \text{ (THICKNESS)}$$

NUMBER OF DATA= 11

STANDARD DEVIATION OF Y = .0603

STANDARD ERROR OF ESTIMATE
 (OR EFFECTIVE SCATTER ABOUT THE LINE) = .0429

R-SQUARED STATISTIC= 49.44

95 PERCENT T FACTOR= 1.833

95 PERCENT CONF.
 LIMITS ON B(1) ARE 1.4157 AND 1.5407
 AND ON B(2) ARE .6764 AND 2.3868

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS MEAN RATIO REDUCED RATIO

.012	1.496	1.443
.024	1.514	1.470
.035	1.532	1.496
.047	1.550	1.521
.059	1.568	1.543
.070	1.586	1.562
.082	1.604	1.577
.094	1.622	1.589
.106	1.640	1.600
.118	1.658	1.609
.129	1.676	1.618
.141	1.694	1.627
.153	1.712	1.636
.165	1.730	1.644
.176	1.748	1.652
.188	1.766	1.661

TABLE 16. CONCLUDED

STATISTICS FOR THE PLOT OF BUS(LTI)/TUS(LTI)2.0
VERSUS THICKNESS FOR
II-64L-2SN-4ZR-2MO

REGRESSED LINE IS

$Y = 1.6970 + 3.7715 X \text{ (THICKNESS)}$

NUMBER OF DATA = 11

STANDARD DEVIATION OF Y = .1474

STANDARD ERROR OF ESTIMATE
(OR EFFECTIVE SCATTER ABOUT THE LINE) = .1040

F-SQUARED STATISTIC = 50.24

95 PERCENT T FACTOR = 1.833

95 PERCENT CONF.
LIMITS ON S(1) ARE 1.5453 AND 1.8487
AND ON S(2) ARE 1.6962 AND 2.6469

SIGNIFICANT REGRESSION YES

MEAN AND REDUCED RATIO FOR SELECTED THICKNESSES

THICKNESS MEAN RATIO REDUCED RATIO

.012	1.741	1.612
.024	1.755	1.677
.035	1.830	1.742
.047	1.874	1.803
.059	1.919	1.858
.070	1.963	1.905
.082	2.007	1.942
.094	2.052	1.972
.106	2.096	1.998
.118	2.140	2.022
.129	2.184	2.044
.141	2.229	2.066
.153	2.273	2.087
.165	2.317	2.108
.176	2.362	2.129
.188	2.406	2.150

TABLE 17. REDUCED RATIOS FOR TI-6AL-2SN-4ZR-2MO SHEET

Ratio	E/D Ratio	Thickness Range, Inches			
		≤0.046	0.047-0.093	0.094-0.140	0.141-0.187
CYS(L)/TYS(LT)		1.062	1.062	1.062	1.062
CYS(LT)/TYS(LT)		1.059	1.059	1.059	1.059
EYS(LT)/TYS(LT)	1.5	1.369	1.369	1.369	1.369
EUS(LT)/TUS(LT)	1.5	1.443	1.521	1.589	1.627
EYS(LT)/TYS(LT)	2.0	1.621	1.621	1.621	1.621
EUS(LT)/TUS(LT)	2.0	1.612	1.803	1.972	2.066

TABLE 18. E_c/E RATIOS FOR TI-6AL-2SN-4Zr-2MO SHEET

IDENTIFICATION	RT AVG	$\frac{E_c}{E}$
0.030 IN. HT. NO. N-9882	17.1	108.8
0.040 IN. HT. NO. N-6112	17.3	115.2
0.050 IN. HT. NO. P-2389	16.4	112.8
0.055 IN. HT. NO. P-4426	17.5	110.9
0.063 IN. HT. NO. P-4426	17.3	111.6
0.071 IN. HT. NO. 6107C7-33-2	15.8	111.4
0.080 IN. HT. NO. 890423-15-5	16.4	109.8
0.090 IN. HT. NO. 890462-34-4	17.1	108.9
0.100 IN. HT. NO. 8907D-10-1	17.3	108.1
0.125 IN. HT. NO. 80078-19-1	17.8	103.9
	NUMBER	10
	AVG R	109.1

TABLE 19. EFFECT OF TEMPERATURE ON COMP. YIELD STRENGTH OF TI-6AL-2SN-4ZR-2MO SHT

IDENTIFICATION	KT AVG	400F	600F	800F	PERCENT R-T AT INDICATED TEMPERATURE
0.050 IN. HT. NO. 0-9A02	153.0	76.9	67.3	64.3	58.1
0.000 IN. HT. NO. 090423-19-5	154.3	74.9	67.4	64.4	55.2
0.125 IN. HT. NO. 000706-09-1	150.4	75.7	67.3	63.3	56.1
0.040 IN. HT. NO. V-3016 REF (1)	149.6	74.4	66.6	64.5	57.0
0.040 IN. HT. NO. V-3016 REF (1)	146.4	73.3	66.1	60.9	57.0
NUMBER R	5	5	5	5	5
AVG R	75.0	67.0	63.3	63.3	56.3
SUM R	375.0	334.0	316.5	316.5	281.5
SUMSQ R	24159.5	22417.9	20043.3	20043.3	15853.8
SQV R	1.3263	0.5501	1.4198	1.4198	1.5945
SDV R	0.5931	0.2460	0.6350	0.6350	0.7131
PERCENT RT	73.6	66.4	61.0	61.0	54.6

TABLE 20. EFFECT OF TEMPERATURE ON COMP MODULUS OF TI-6AL-2SN-4ZR-2YO SHEET

IDENTIFICATION	RT AVG	PERCENT R-T AT INDICATED TEMPERATURE				
		400F	600F	800F	1000F	
J.050 IN.HT.NO.N-9802	18.5	96.2	90.3	84.9	80.0	
0.060 IN.HT.NO.890423-15-5	18.0	93.9	85.3	82.6	72.2	
0.125 IN.HT.NO.800736-09-1	18.5	93.0	87.6	82.2	74.6	
0.040 IN.HT.NO.V-3016 REF (1)	14.2	89.4	85.2	79.6	74.6	
0.040 IN.HT.NO.V-3016 REF (1)	14.5	86.2	79.3	75.9	70.3	
NUMBER R	5	5	5	5	5	
AVG	91.7	86.1	81.0	74.4		





Figure 29. Tensile Specimen



- Notes: 1 Ends must be flat and parallel to within 0.0002".
 2 Surface must be free from nicks and scratches.

Figure 30. Compression Specimen





Figure 31. Shear Specimen



With e/D of 1.5, $a=0.375''$
 e/D of 2.0, $a=0.500''$

Figure 32. Bearing Specimen




Figure 33. Location of Test Specimens, 0.030, 0.040, 0.055, 0.063, and 0.071-inch Thick Sheet




Figure 35. Location of Test Specimens, 0.090-inch Thick Sheet




Figure 36. Location of Test Specimens, 0.100-inch Thick Sheet




Figure 37. Location of Test Specimens, 0.125-inch Thick Sheet




Figure 38. Plot of BUS(LT)/TUS(LT), e/D = 1.5, Ratios




Figure 39. Plot of BUS(LT)/TUS(LT), e/D = 2.0, Ratios




Figure 40. Working Curve Showing the Effect of Temperature on Compressive Yield Strength of Ti-6Al-2Sn-4Zr-2Mo Duplex Annealed Sheet




FIGURE 5.3.3.2.1. Effect of temperature on the compressive yield strength (F_{cy}) of duplex annealed Ti-6Al-2Sn-4Zr-2% alloy sheet.

Figure 41. Proposed MIL-HDBK-5 Figure 5.3.3.2.1




Figure 5. Effect of temperature on the tensile modulus (E) of single, duplex, and triplex annealed Ti-6Al-2Sn-1Zr alloy.

Figure 4. Comparison of Percentages with Existing E Curve




Figure 5.3.3.1.4. Effect of temperature on the tensile and compressive moduli (E and E_c) of single, duplex, and triplex annealed Ti-6Al-2Sn-4Zr-2Mo alloy.

Figure 43. Proposed MIL-HDBK-5 Figure 5.3.3.1.4

APPENDIX A

TEST PROCEDURES

Tension

Procedures used for tension testing were those recommended in ASTM Method E8 and E21. Tensile tests were conducted using Baldwin Universal-type testing machines. These machines are calibrated at frequent intervals in accordance with ASTM Method E4 to assure loading accuracy to within 0.2 percent. The machines are equipped with integral automatic strain pacers and autographic strain recorders.

The extensometers used conformed to ASTM E53 classification B1 having a sensitivity of 0.0001 in./in. The strain rate in the elastic region was maintained at 0.005 in./in./min. After yielding occurred, the rate was increased to approximately 0.1 in./in./min. until fracture. Ultimate strength, yield strength (0.2 percent offset), and elongation were determined. The yield strength was determined from the load-strain curves. Tensile tests were conducted at room temperature only.

Compression

Procedures for conducting compression tests conformed to ASTM Method E9 along with the temperature control provisions of E21. Specimens tested at elevated temperatures in the Baldwin universal testing machines were heated in standard wire-wound resistance furnaces. Each furnace was equipped with a Foxboro controller capable of maintaining the test temperature to within 5 F of the control temperature. Chromel-Alumel thermocouples were attached to the specimen gage section and used to monitor temperatures. For sheet specimens, thermocouples were approximately 1/16 inch from edge of specimen. Each specimen was soaked at temperature for about 20 minutes before being tested. Extensometer and strain rates were similar to those described in tension testing section. The compressive yield strength (0.2 percent offset) was derived from the load-strain curves.

Shear

Shear tests were performed in a Baldwin universal-type testing machine. Shear tests were conducted at room temperature only.

Bearing

Bearing tests were conducted in accordance with ASTM Method E138. All bearing tests were performed in electrohydraulic servocontrolled testing machines. Deformation of the bearing hole was measured with a differential-transformer extensometer and recorded versus load with a conventional autographic recorder. The hardened steel bearing pin was rotated so that a new

bearing surface was used for each specimen. Prior to testing, the pins, specimens, and fixture were ultrasonically cleaned in acetone. After cleaning, white gloves were used in the handling of pins, specimens, and fixtures. Bearing ultimate strength and bearing yield strength (2 percent of pin diameter offset) were determined from the load-strain curves. Bearing tests were conducted at room temperature only.