

Evaluation of Molybdate Conversion Coatings for Aluminum Alloys by Electrochemical Impedance Spectroscopy

L. M. Calle

National Aeronautics and Space Administration, YA-F2-T, Kennedy Space Center, FL 32899, US; (author for correspondence)

L. G. MacDowell

National Aeronautics and Space Administration, YA-F2-T, Kennedy Space Center, FL 32899, US

Abstract

Electrochemical impedance spectroscopy (EIS) was used to investigate the corrosion inhibiting properties of proprietary molybdate conversion coatings on aluminum alloy 2024-T3 in aerated 5% (w/w) NaCl. Corrosion potential and EIS measurements were gathered for six formulations at several immersion times for two weeks. The conversion-coated alloy panels showed an increase in the corrosion potential during the first 24 hours of immersion that later subsided and approached a steady value. The EIS spectra of the conversion-coated alloy were characterized by impedance that is higher than the impedance of the bare alloy at all the immersion times. The low frequency impedance, Z_{16} for the conversion-coated alloy was higher at all the immersion times than that of the bare panel. This indicates improvement of corrosion resistance with addition of the molybdate conversion coating. Scanning electron microscopy (SEM) revealed the presence of cracks in the coating and the presence of cubic crystals believed to be calcium carbonate. Energy dispersive spectroscopy (EDS) revealed the presence of high levels of aluminum, oxygen, and calcium but did not detect the presence of molybdenum on the test panels. X-ray photoelectron spectroscopy (XPS) indicated the presence of less than 0.01 atomic percent molybdenum on the surface of the coating.

Keywords

EIS, Molybdate Conversion Coating, Aluminum 2024-T3, Corrosion, alloy, Coatings

1. Introduction

Chromate conversion coatings have been used for the protection of aluminum alloys for over 70 years. Although their efficiency in minimizing corrosion attack is excellent, there are health and safety concerns over their use due to their toxicity and carcinogenic nature. Despite an extensive research effort over the past decade, a completely satisfactory replacement for chromate conversions coatings has yet to be identified.

Hexavalent molybdenum has received attention recently as a replacement for chromate conversion coatings. Molybdate mimics chromate in a variety of applications but it exhibits significantly lower toxicity.¹ Several proprietary molybdate conversion coatings have been developed for NASA. Six proprietary formulations of the coatings on aluminum alloy 2024-T3 were available for characterization by Electrochemical Impedance Spectroscopy (EIS).



2. Experimental Procedures

2.1 Test Samples

Six proprietary formulations (labeled A-F) were provided by Lynntech, Inc. (College Station, Texas). Panels of aluminum 2024-T3 alloy (with average composition of 4.4% Cu, 0.6% Mn, 1.5% Mg, and 93.5% Al) were cut to a size of 10.16 cm ? 15.24 cm and treated with a formulation of the molybdenum conversion coating.

2.2 Corrosion Potential Measurements

Corrosion potential measurements were performed using a system manufactured by EG&G Princeton Applied Research Corporation. The system used includes: (1) the Model 273 Computer-Controlled Potentiostat/Galvanostat, (2) the Model 5210 Computer-Controlled Lock-In Amplifier, and (3) the Model 352 SoftCorrTM III Corrosion Measurement Software . The electrochemical cell included a saturated Calomel electrode, SCE, a platinum counter electrode, the sample working electrode, and a bubbler/vent tube. Three electrochemical cells were used. The flat specimen holders exposed a surface area of 1 cm², 13 cm², or 32 cm² depending on the cell that was used. Corrosion potential values were gathered for one hour in aerated 5% (w/w) NaCl before the first set of EIS measurements was obtained. Subsequent corrosion potential values were collected before each set of EIS measurements which were collected at several time intervals up to a maximum of 168 hours. All solutions were prepared using deionized water.

2.3 Electrochemical Impedance Measurements

A Model 378 Electrochemical Impedance system manufactured by EG&G Princeton Applied Research Corporation was used for all EIS measurements. The system includes: (1) the Model 273 Computer-Controlled Potentiostat/Galvanostat, (2) the Model 5210 Computer-Controlled Lock-In Amplifier, and (3) the Power Sine Electrochemical Impedance Software. Data were gathered in the frequency range from 100 kHz to 0.01 Hz. The AC amplitude used for the experiments was 10 mV. Each sample was studied at various immersion times in aerated 5% (w/w) NaCl for up to one week.

Bode magnitude plots of the data (showing the logarithm of the modulus of the impedance, log? Z?, as a function of the logarithm of frequency and phase angle, alpha in degrees, as a function of the logarithm of frequency) as well as Nyquist plots (showing the negative of the imaginary component of impedance as a function of the real component of the impedance) were obtained for each formulation.

2.4 Scanning Electron Microscopy (SEM)/Energy Dispersive Spectroscopy (EDS)

SEM examinations were carried out on a JEOL JSM-6100 scanning electron microscope at 5.0 to 25.0 kV. Phase identification was done using EDS in SEM with a Kevex SI(LI) detector.



2.5 X-ray Photoelectron Spectroscopy (XPS)

Samples were analyzed with a Kratos XSAM800 X-ray photoelectron spectrometer with argon etching between analyses (for a total of 40 minutes).

3. Results and Discussion

3.1 Corrosion Potential Measurements

Corrosion potential values gathered during the hour immediately preceding the first set of EIS measurements for each molybdate formulation indicated that an hour was sufficient to allow the potential to equilibrate. Subsequent values of the corrosion potential were obtained immediately before each set of EIS measurements was collected. Figure 1 shows the change in corrosion potential with immersion time for all formulations of the molybdate conversion-coated panels and for a bare aluminum alloy panel. The coated panels showed a steady increase in the corrosion potential towards the corrosion potential of the aluminum alloy during the first 24 hours of immersion. A gradual increase in corrosion potential with immersion time is expected if the coating encourages slow but uniform (i.e., pit free) growth of the oxide layer. This behavior was observed for all formulations. The initial increase in the corrosion potential subsided and after 48 hours of immersion a steady value of the corrosion potential was obtained. Panels coated with formulations A, D, and F achieved a corrosion potential slightly higher than the corrosion potential of the aluminum alloy while panels B, C, and E achieved a corrosion potential that was lower. A shift of the corrosion potential of the alloy in the positive direction is indicative of the presence of a protective effect on the aluminum alloy. Visual inspection of the panels revealed that panels A,D, and F had the fewest number of corrosion spots per cm².





Figure 1. Corrosion potential as a function of immersion time in 5% (w/w) NaCl

3.2 Electrochemical Impedance Spectroscopy

Figure 2 shows representative impedance spectra (Bode format: The phase angles have been omitted for clarity) for formulation A and for aluminum 2024-T3 at various immersion times The impedance of the coated alloy is greater than the impedance of the bare alloy at all frequencies. The higher value of the impedance is indicative of the improvement of corrosion resistance with the addition of the molybdate conversion coating.

The low-frequency impedance, $Z_{\rm f}$ (determined from data at 0.05 Hz), has been proposed as the optimal EIS parameter to evaluate the performance of corrosion inhibiting coatings on aluminum.² The impedance at this frequency includes the response of the coating as well as part of the response of the oxide and/or corrosion product in the pores at the metal interface. $Z_{\rm ff}$ reflects the condition of the substrate as well as that of the coating. Although the $Z_{\rm ff}$ values do not give information about how a coating degrades (i.e., water uptake, blistering, etc.), they correlate with coating performance. Figure 3 shows the variation of $Z_{\rm ff}$ with immersion time for the molybdate-coated as well as the bare aluminum alloy. $Z_{\rm ff}$ values for the molybdate coated panels are in the order of $10^3 - 10^5$? cm² while those for the bare panel are of the order of 10^3 ? cm². Low frequency impedance for chromate conversion coatings on aluminum alloy 2024 after 3 hours of immersion in aerated 0.5 M (3%) NaCl have been reported³ as being in the order of 10^4 ? cm². This value is lower than 10^{10} ? cm² which is the value expected of an excellent barrier coating.⁴





Figure 2. Bode plots for formulation A and aluminum alloy at different immersion times



Figure 3. Low frequency impedance Z_{if} as a function of immersion time in NaCl 5% (w/w) NaCl

Impedance data in the Nyquist format were analyzed using the simplified equivalent circuit shown in Figure 4. This circuit gives a coating resistance (R_c) which can be used as a figure of





Figure 4. Simplified circuit for conversion-coated aluminum alloys⁵

merit to assess coating performance. Values for R_c for each conversion-coated and for the bare panel are shown in Figure 5. The conversion-coated panels achieved R_c values in the 10^4 - 10^5 ? cm² range while the bare aluminum alloy panel had R_c values in the order of 10^3 ? cm².



Figure 5. Apparent integrated resistance as a function of immersion time

The threshold R_c value⁵ proposed to define the minimum value for which a given coating can be expected to attain a passing result in a 168-hour salt spray test for aluminum 2024-T3 is 2 ? 10^6 ? cm² to 5 ? 10^6 ? cm². None of the conversion-coated panels attained these values despite their successful performance in salt fog testing. However, the reliability of salt spray results as well as the use of EIS data for prediction of salt spray performance has been challenged by Mansfeld.⁶

3.3 SEM/EDS

SEM of the of one of the conversion coated panels (formulation A) revealed the presence of cracks on the coating as well as the presence of cubic crystals (see Figure 6). EDS analysis of the crystals indicated the presence of high concentrations of calcium as well as oxygen (see Figure 7). This information can be interpreted as evidence of the presence of calcium carbonate on the coating.





Figure 6. SEM micrograph of conversion-coated (formulation A) aluminum alloy



Figure 7. EDS spectrum of conversion-coated (formulation A) aluminum alloy

EDS analysis did not detect the presence of molybdenum in the coating. This finding can be attributed to the fact that EDS is sensitive to most elements if they are present above 0.4% by weight.

3.4 XPS



The conversion-coating was further analyzed by x-ray photoelectron spectroscopy (XPS) with argon etching between analyses. The sample showed a small peak in the XPS spectrum that corresponded with the expected location of a molybdenum peak. This would amount to less than 0.01 atomic percent molybdenum on the surface of the sample.

4. Conclusions

Corrosion potential measurements indicated that formulations A, D, and F exhibit a protective effect on aluminum 2024-T3.

EIS results for the six formulations tested showed that there is an improvement in the corrosion resistance of aluminum 2024-T3 with the addition of the molybdate conversion coating.

SEM/EDS revealed the presence of cracks in the coating. Cubic crystals of what it is believed to be calcium carbonate were also observed on the surface of the coating. SEM/EDS failed to detect the presence of molybdenum in the coating.

XPS analysis of the coating indicated that there is less than 0.01 atomic percent molybdenum on the surface of the sample.

Further analysis of the EIS data as well as data gathered from atmospheric exposure of the panels are suggested before more definite conclusions can be drawn.

4. Aknowledgements

The authors gratefully acknowledge Lynntech, Inc. (College Station, Texas) for providing the test panels. The authors also acknowledge the technical support of Claudia Amorim with the EIS measurements, Virginia Cummings, Steve McDanels and Stan Young with the SEM and EDS analysis, and Dr. Mike Hampton for the XPS analysis.

5. References

- 1. B.A. Shaw, G.D. Davis, T.L. Fritz, and K.A. Oliver, J. electrochem. Soc., 137 (1990): p. 359.
- 2. J.A. Grandle and R.S. Taylor, Corrosion, 50 (1994): p. 792.
- 3. J.E.O. Mayne, and D.J. Mills, J. Oil & Colour Chemists Assoc., 58 (1975) p. 155.
- 4. R. G. Buchheit, M.D. Bode, and G.E. Stoner, Corrosion, 50 (1994): p. 205.
- 5. R.G. Buchheit, M. Cunningham, H. Jensen, M.W. Kendig, and M.A. Martinez, Corrosion, 54 (1998): p. 61.
- 6. F. Mansfeld, Corrosion, 54 (1998): p. 595.