

NOT MEASUREMENT SENSITIVE

MIL-H-6088G
AMENDMENT 1
15 September 1992

MILITARY SPECIFICATION
HEAT TREATMENT OF ALUMINUM ALLOYS

This amendment forms a part of MIL-H-6088G, dated 1 April 1991, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 7

3.7.2.2: Delete and substitute:

"3.7.2.2 Quenching 2XXX and 7XXX forgings other than 2014 and 2024. Forgings of these alloys shall be quenched by total immersion in water heated to 140-160°F unless quenchants other than hot water are necessary to achieve required properties or to minimize residual tensile stresses and/or distortion."

Custodians:
Army - MR
Navy - AS
Air Force - 11

Preparing activity:
Navy - AS
(Project 95GP-0392)

Reviewer activities:
Army - AR, AV
Navy - SH
Air Force - 99
DLA - IS
MISC - MS
MISC - NA (MSC)

User activities:
Army - ME
Navy - OS